Application Serial No: 10/730,194 In reply to Office Action of 9 March 2005 Attorney Docket No. 84280

## AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

## Listing of Claims

- 1. (cancelled)
- 2. (cancelled)
- 3. (currently amended) The method in accordance with claim 2 A frequency domain method to estimate a real and imaginary dilatational wavespeed of a material, said method comprising the further step steps of:

providing a specimen of the material;

providing a source of acoustic waves at a zero wavenumber;

positioning said specimen at a distance from said source such that said acoustic waves conform to plane waves;

exciting said specimen with said acoustic waves for at least two nonzero wavenumbers;

Application Serial No: 10/730,194 In reply to Office Action of 9 March 2005 Attorney Docket No. 84280

- measuring frequency domain transfer function data

  subsequent said excitation of said specimen for at

  least two nonzero wavenumbers;
- calculating said frequency domain transfer function data to

  closed form subsequent to said measuring step of said

  specimen for said excitation for at least two nonzero

  wavenumbers;
- of said specimen from said calculated frequency domain
  transfer function data;
- determining an estimated real and imaginary shear wavespeed

  of the material from said frequency domain transfer

  function data calculated to closed form subsequent to

  said measuring step of said specimen for said

  excitation for at least two nonzero wavenumbers; and
- obtaining a real and imaginary shear modulus using a grid method of the material from said real and imaginary determined shear wavespeed.

Application Serial No: 10/730,194 In reply to Office Action of 9 March 2005 Attorney Docket No. 84280

- 4. (original) The method in accordance with claim 3, said method comprising the further step of determining a real and imaginary Young's modulus of the material from said obtained shear modulus.
- 5. (original) The method in accordance with claim 4, said method comprising the further step of obtaining an estimated Poisson's ratio of the material from said determined Young's modulus and said obtained shear modulus.